


## Dyna- SPA

Simulationsgerät für Abrieb, Kratzer sowie Schlägen





Oberflächenschäden durch Abrieb, Kratzer oder Schläge gehören zu den häufigsten Ursachen von Störungen in der Produktqualität. In vielen realen Anwendungen treten tiefe Kratzer oder schwerer Abrieb bei einer schnellen und hoch dynamischen Bewegung auf, zum Beispiel ein tiefer, langer Kratzer im Autolack durch einen Schlüssel. Dieser Kratzer wird mit bis zu 100 cm/s erzeugt.

**Dyna -SPA®**, ist das einzige Gerät, das die Simulation der schnellsten und dynamischen Kratz-, Schlag-, und Abriebbelastungen in einer Maschine ermöglicht - bei freier Wahl von Geschwindigkeit und Richtung. Jeder lineare Kratz- oder Abriebtest mit einer Geschwindigkeit von bis zu 150 cm/s, Prüfkräften von bis zu 30 N und einem Reibweg von bis zu 120 mm ist möglich. Der Dyna-SPA® erfüllt über 30 internationale Standards (ASTM/DIN/ISO) für folgende Anwendungen:

#### Abrieb

- Universalabriebtest
- Schuhsohlentest
- Crockmeter Test
- Draht/Kabelabriebtest
- Film/Verpackungsmaterial
- Magnetbandabriebtest
- Wasch-/Scheuerschwamm  
Abriebtest
- Zahn Abriebtest
- Scheuerabriebtest

#### Kratzer

- Universalkratztest
- Fingernagelkratztest
- Stifttest
- Schlüsselkratztest

#### Schlagtest

- Universal Schlagtest
- Fingerspitzen Schlagtest

#### Vorteile

- Schnellstes System zur Durchführung von Kratz-, Schlag- oder Abriebprüfungen
- Hoch dynamisch, lineare Bewegung mit bis zu 200 cm/s
- Prüfungen nach über 30 Standards:  
ASTM/ISO/DIN/EN
- Industrielle Anwendung: Simulation von realem Abrieb, Schlägen und Kratzern
- Universelle Funktionalität durch modulares Design
- Reproduzierbare Ergebnisse dank vorgegebener Teststandards
- Reproduzierbare Gitterschnittprüfung

---

Ihr Ansprechpartner:

**Richard Hess MBV GmbH**  
Gildestrasse 5

47665 Sonsbeck  
Tel. 02838 / 444 0. 1770  
Internet: [www.hess.mbv.de](http://www.hess.mbv.de)  
E-Mail: [info@hess-mbv.de](mailto:info@hess-mbv.de)



# Dyna-SPA®

**Highest Dynamic Speed with Longest Stroke for  
Simulation of:**

- Universal Abrasion
- Universal Scratch
- Universal Punch
- and many more

## Basic Function

Damage to a surface due to abrasion, scratch, mar, scrape and punch is one of the main reasons for the disturbance of a product's quality. In many real applications, deep scratch or severe abrasion occurs during a fast and high dynamic motion, e.g. a deep long scratch by a key on the exterior paint of a car, and this high dynamic scratch occurs at a high speed up to 100 cm/s.

*Dyna -SPA®*, is the only machine which can simulate the fastest and dynamic scratch, punch and abrasion tests within one machine with freely programmable speed (up to 100 cm/s) and stroke (up to 120mm). It complies with over 30 international standards (ASTM/DIN/ISO) for the following applications:

### SCRATCH:

- Universal Scratch Test
- Nail Scratch Test
- Pencil Test
- Key Scratch Test
- Cross-cut Test


### PUNCH:

- Universal Punch Test
- Fingertip Punch Test

### Mar Test & Adhesion Test

### ABRASION:

- Universal Abrasion Test
- Shoe Sole Test
- Crockmeter Test
- Wire/Cable Abrasion Test
- Film/Packaging Material Abrasion Test
- Magnetic Stripe Abrasion Test
- Cleaning/Scouring Pad Abrasion Test
- Tooth Abrasion Test
- Scuffing Abrasion Test



## Technical Specification

Model	<i>Dyna -SPA®</i>		
Features	Scratch	Abrasion	Punch
Static Load	1-30 N		
Stroke Length	max. 120 mm (programmable)		
Linear speed	up to 100 cm/s (higher speed upon request)		
Cycles	1-10,000,000		
Measurement delay (s)	programmable		
Speed in & out	programmable		
Power supply	230V / 50 Hz ; 110V / 60 Hz		
Compressed air	6 bar, external, oil free, water free		
Accessories included with the base unit	3 different loads; 2 scratch tips; 1 punch tip (metal)  1 universal clamp for abrasion test  1 set of sample holding plate		
	* All the above accessories will be packed in one box; the base unit will be packed in a wooden box acc. to international shipment.		
It is up to the user to determine a suitable adapter, tip or sample clamp appropriate to their products.			

## Maintenance and Services


*Dyna -SPA®* should be inspected, maintained and calibrated minimum once a year. Some of the spare parts such as abradants are required to be replaced frequently.

## Test Principle

**Dyna -SPA®** tester is designed to test either flat surfaces or curved products, making it versatile to evaluate finished products of all sizes and all materials. A variety of optional test tips, test textiles, test media and sample clamps is provided to perform different types of abrasion, scratch, mar and punch tests. And it is also suitable for both wet and dry tests.

**Dyna -SPA®** tester is built with a horizontal piston rod driven by a pneumatic cylinder that moves in a linear motion, either one-direction or reciprocating. At the end of the cylinder is a movable assembly which allows the cylinder and the arm to move freely in the Z-direction. Therefore, the tip follows the shape and surface structural. The tip is mounted to the end of the piston rod and a dead weight is mounted on the top to generate a load in Z-direction onto the test sample. As the horizontal rod moves, the test tip raises or lowers vertically to follow the curvature of the test sample. In addition, the pillow block can be moved up and down, therefore the samples with a wide range of thicknesses can be tested.


### Mode 1



### One-Direction Mode

- Pneumatic system drives the tip wheel to the prepositioning point “2” to ensure the right velocity for the test;
- Then the tip is moving from point “2” with a certain stroke to point “3” at pre-defined speed;
- A pushup rod will lift the pneumatic cylinder to position “4” and reside back at the position “2” for the next cyclic linear motion;
- An opposite cycle from position “2” to “4” to “3” can also be achieved.


### Mode 2



### Reciprocating Mode

- Pneumatic system drives the tip wheel to the prepositioning point “2” to ensure the right velocity for the test;
- Then the tip is moving back and forth between point “2” and “3” at pre-defined speed, the inward and outward speeds can be different.

### Mode 3



### Punch Test Mode

- Pneumatic cylinder is flipped 180°;
- Then the punch tip is hitting the sample back and forth between point “1” and “2” at pre-defined speed.

## Software

*Dyna -SPA®* tester has an adjustable program which enables the user to select the test mode, test speed, struck length, test load and others. According to the test method, the test condition can be set up freely in the software.

<b>PUNCH</b>  <b>SCRATCH</b> <b>ABRASION</b>  	<b>ABRASION TEST</b> <b>Touch</b>  Start: <input type="text" value="40"/> End: <input type="text" value="60"/> Speed Out: <input type="text" value="80"/> Speed In: <input type="text" value="70"/> Delay Start(s): <input type="text" value="0"/> Delay End(s): <input type="text" value="0"/> Cycles: <input type="text" value="300"/>  <table border="1" style="margin-left: auto; margin-right: auto;"> <tr> <td>1</td><td>2</td><td>3</td></tr> <tr> <td>4</td><td>5</td><td>6</td></tr> <tr> <td>7</td><td>8</td><td>9</td></tr> <tr> <td>0</td><td colspan="2">SAVE</td></tr> </table> <input type="button" value="LOAD"/> <input type="button" value="TEST"/> <input type="button" value="START"/> <input type="button" value="BACK"/>	1	2	3	4	5	6	7	8	9	0	SAVE	
1	2	3											
4	5	6											
7	8	9											
0	SAVE												

## Test Methods

*Dyna -SPA®* tester can perform various tests which comply with many ISO, ASTM, BS, GB/T standards. Please contact us for information on the test standards that can be performed by *Dyna -SPA®* to evaluate the resistance of a material surface to scratch, abrasion, mar, scrape and punch.


## Adapters

There is a variety of adapters within the *Dyna -SPA®*, for example, key scratch, cross cut scratch, crockmeter abrasion, and many more.




### Key Scratch Adapter

- Standardised key scratch tip;
- Can be used for simulation of scratch/abrasion resistance of the magnetic stripe of the credit card.



### Shoe Sole Scratch Adapter

- Standardised shoe sole tip;
- Leather or SBR material:
  - I. Shore-hardness ( $95 \pm 3$ ) Shore A
  - II. Spec. weight ( $1.23 \pm 0.20$ ) g/cm<sup>3</sup>
  - III. Tensile strength  $\geq 10$  N/mm<sup>2</sup>
  - IV. Elongation  $\geq 250$  %
  - V. Abrasion  $\leq 250$  mm<sup>3</sup> acc. to DIN ISO 4649



### Shoe Sole Abrasion Adapter

- Standardised shoe sole tip;
- Specified shore hardness
- 20mm diameter
- for testing the floor abrasion resistance, car interior carpet abrasion resistance and many more


## Tip Options

A great choice of tips is supplied with each *Dyna -SPA®* tester along with necessary abradands and liquid media. Each tip is standardised in many parameters including the size, shape and materials which permits the equivalent result. A detailed tip choice of *Dyna -SPA®* is described in details upon request.

## Sample Clamp Options



Universal Sample Clamp for flat and curved samples with various height



Clamp for testing specific area

Other clamp choice is available upon request.

## Technical Specification

Model	<i>Dyna -SPA®</i>		
Features	Scratch	Abrasion	Punch
Static Load	1-30 N		
Stroke Length	max. 120 mm (programmable)		
Linear speed	up to 100 cm/s (higher speed upon request)		
Cycles	1-10,000,000		
Measurement delay (s)	programmable		
Speed in & out	programmable		
Power supply	230V / 50 Hz ; 110V / 60 Hz		
Compressed air	6 bar, external, oil free, water free		
Accessories included with the base unit	3 different loads; 2 scratch tips; 1 punch tip (metal)  1 universal clamp for abrasion test  1 set of sample holding plate		
	* All the above accessories will be packed in one box; the base unit will be packed in a wooden box acc. to international shipment.		
It is up to the user to determine a suitable adapter, tip or sample clamp appropriate to their products.			

## Maintenance and Services

*Dyna -SPA®* should be inspected, maintained and calibrated minimum once a year. Some of the spare parts such as abradants are required to be replaced frequently.